

Insulthane® Lift 3LB | Closed-Cell Lifting Foam

Product Description

Insulthane® Lift 3LB is a two-component, closed-cell, rigid structural polyurethane foam system, intended for slab jacking, concrete lifting and other slab stabilization applications. Insulthane® Lift 3LB has excellent expansion and superior strength, making it a great option for concrete lifting needs. Insulthane® Lift 3LB is available in both a “regular” and “fast” formula depending on project requirements.

Recommended Uses

- Concrete slab, road, and runway lifting
- Cavity/void fill
- Unconsolidated soil stabilization
- Concrete slab stabilization
- Geo-technical applications
- Ditch damming
- Mine and tunnel decommissioning
- Pipe, tank, and well decommissioning

Features

- Minimal heat generation during application allows for thick lifts
- No ozone depleting products (ODP)
- No bromine or formaldehyde components
- Mildew, bacteria, and fungus resistant
- Contains renewable resource components

Packaging

This product is sold in standard 100 gallon drum sets and 500 gallon tote sets. Non-standard containers may require a longer lead time.

Storage and Handling

Store in a dry location between 10-32°C (50-90°F). Keep drums tightly sealed and stored out of direct sunlight when not in use.

Processing Equipment

A standard 1:1 ratio, heated plural component equipment developing a minimum of 1100 psi (7.58 MPa) dynamic pressure with heating capabilities to 66°C (150°F) will adequately process this product. Primary heater temperature should be 43°C - 55°C (110°F - 130°F). Extreme care must be taken when removing and reinstalling drum transfer pumps so as NOT to reverse the “A” and “B” components.

Limitations

This product is for professional use only. Minimum material/container temperature for application is 21°C (70°F). Apply product when surface and air temperatures are above 5°C (40°F) and the surface temperature is at least 3°C (5°F) above dew point. Maximum service temperature; constant 93°C (200°F). For large void fill applications, care must be taken not to inject too much foam in a single pass.

Density Information

Attribute	Test	Results
Density (Nominal)	ASTM D1622	3 lb/ft ³
Free Rise Core	ASTM D1622	2.9 - 3.2 lb/ft ³
Confined (In-Place) Density	-	3.2 - 3.5 lb/ft ³ (Estimated)
Free Rise Compressive Strength	ASTM D1621	41 psi

In place density and compressive strength is dependant on several variables including lift thickness, processing parameters and surface temperature.

Reactivity Information @ 25°C (77°F)

Attribute	Time (Regular)	Time (Fast)
Cream Time	7 - 10 seconds	5 - 7 seconds
Rise Time	40 - 45 seconds	30 - 40 seconds

Liquid Properties

Attribute	Part A (ISO)	Part B (Resin)
Mix Ratio, by volume	1	1
Weight per gallon (approx.)	10.3 lbs (4.67 kg)	8.8 - 9 lbs (4 - 4.08 kg)
Viscosity @ 25°C (77°F)	180 - 220 cps	500 - 800 cps
Colour	Amber	Light Yellow
Shelf Life	12 months	

DISCLAIMER: This data is based on information believed to be reliable and is offered solely for evaluation. Elastochem Specialty Chemicals Inc.'s products are sold with the understanding that the Buyer determines the suitability of this product for its particular application. Product owner assumes all risk for misuse of the materials. Use of this product is beyond the control of the Seller, the Buyer assumes all risks of use or handling. Elastochem Specialty Chemicals Inc. assumes no liability for mis-application or any other error or omission of applicator. For warranty conditions refer to terms listed in Elastochem Manufacturer's Defect Warranty. Contact your Elastochem representative for more details.



Elastochem Specialty Chemicals Inc.
37 Easton Road Brantford, ON N3P 1J4
1-877-787-2436 www.elastochem.com

